


AD-A120 837

HIGHLY CONDUCTING IODINE-DOPED FLUOROALUMINUM AND
FLUOROGALLIUM NAPHTHALO. (U) CASE WESTERN RESERVE UNIV
CLEVELAND OHIO DEPT OF CHEMISTRY L A SCHECHTMAN ET AL.
20 OCT 82 CWRU/DC/TR11 N00014-75-C-0693 F/G 11/9

1/1

UNCLASSIFIED

NL



END

F/G 11/9

N00014-75-C-0693

CWRU/DC/TR11

20 OCT 82

CLEVELAND OHIO

DEPT OF CHEMISTRY

L A SCHECHTMAN ET AL.


(U)

FLUOROGALLIUM NAPHTHALO.


HIGHLY CONDUCTING IODINE-DOPED FLUOROALUMINUM AND

AD-A120 837

UNCLASSIFIED




MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A




MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

ADA 120837

DNC FILE COPY

(12)

Unclassified
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report CWRU/DC/TR11	2. GOVT ACCESSION NO. AD-A120837	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Highly Conducting, Iodine-Doped Fluoroaluminum and Fluorogallium Naphthalocyanine Polymers	5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Lee A. Schechtman and Malcolm E. Kenney	8. CONTRACT OR GRANT NUMBER(s) N000140750C-0693	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry Case Western Reserve University Cleveland, OH 44106	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 356-590	
11. CONTROLLING OFFICE NAME AND ADDRESS Department of the Navy Office of Naval Research Arlington, VA 22217	12. REPORT DATE October 20, 1982	
	13. NUMBER OF PAGES 27	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Accepted for publication in J. Electrochem. Soc.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Conducting Polymers, Aluminum Naphthalocyanines, Gallium Naphthalocyanines, Cofacial Polymers, Iodine-Doped Polymers		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Methods for the preparation and some of the properties of the new com- pounds fluoroaluminum and fluorogallium 2,3-naphthalocyanine are described. It is clear on the basis of the data gathered that these fluorides are com- posed of chains having metal-fluorine backbones and cofacial rings. A procedure for the preparation of iodinated species from these fluorides and some of the properties possessed by these species are described. Of particular interest are the relatively high conductivities they show when they have moderate iodine contents. It is concluded that they contain cationic chains		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

82 10 29 027

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

20- (cont.)

having metal-fluorine backbones and cofacial rings, triiodide and pentaiodide ions, and, possibly, uniodinated chains. Additional conclusions related to the ability of these species to conduct are discussed. Factors which in general may or do influence the conductivity of cofacial conducting polymers are also discussed.

20- 2
100 8 190
H

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

OFFICE OF NAVAL RESEARCH

Contract N00014-75-C-0693

Task No. 356-590

TECHNICAL REPORT NO. 11

**Highly Conducting, Iodine-Doped Fluoroaluminum and
Fluorogallium Naphthalocyanine Polymers**

by

Lee A. Schachtman and Malcolm E. Kenney

Accepted for Publication

in the

Journal of the Electrochemical Society

**Case Western Reserve University
Department of Chemistry
Cleveland, OH 44106**

October 20, 1982

**Reproduction in whole or in part is permitted for
any purpose of the United States Government**

**This document has been approved for public release
and sale; its distribution is unlimited**

**Highly Conducting, Iodine-Doped
Fluoroaluminum and Fluorogallium
Naphthalocyanine Polymers**

Lee A. Schechtman and Malcolm E. Kenney

**Case Western Reserve University
Cleveland, Ohio 44106**

-1-

Abstract

Methods for the preparation and some of the properties of the new compounds fluoroaluminum and fluorogallium 2,3-naphthalocyanine are described. It is clear on the basis of the data gathered that these fluorides are composed of chains having metal-fluorine backbones and cofacial rings. A procedure for the preparation of iodinated species from these fluorides and some of the properties possessed by these species are described. Of particular interest are the relatively high conductivities they show when they have moderate iodine contents. It is concluded that they contain cationic chains having metal-fluorine backbones and cofacial rings, triiodide and pentaiodide ions, and, possibly, uniiodinated chains. Additional conclusions related to the ability of these species to conduct are discussed. Factors which in general may or do influence the conductivity of cofacial conducting polymers are also discussed.



Accession For	
DTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avall and/or Special
A	

For both theoretical and practical reasons a number of studies have been carried out on conducting polymers over the past few years. Included among the polymers studied have been a series of the cofacial, macrocyclic type (1).

The development of polymers of this type resulted from the merging of two quite different lines of investigation. One of these centered on the synthetic and structural chemistry of metal phthalocyanines and led to the discovery of $(AlPc)_2O$ (2). Later it led to the recognition of the dimeric, μ -oxo bridged nature of this compound (3).

In addition this line of investigation led to the discovery of a number of species closely related to $(AlPc)_2O$. Among these are the μ -oxo bridged oligomers $AlPcOSiPcOAlPc$ (3), $(Me_3SiO)_2MeSiO(SiPcO)_3SiMe(OSiMe_3)_2$ (4,5), $AlPcO(SiPcO)_2AlPc$ (3), and the μ -oxo and μ -fluoro bridged polymers $(SiPcO)_n$ (6), $(GePcO)_n$ (7), $(SnPcO)_n$ (8), $(AlPcF)_n$ (9,10), and $(GaPcF)_n$ (9,10), Figs. 1 and 2.

Various studies of $(SiPcO)_n$ and its germanium and tin analogs and of $(AlPcF)_n$ and its gallium analog, including, for example, electron microscopy studies, showed that these polymers are fully crystalline, rigid-rod polymers (6,8,10,11), Fig. 3, and that their ring-ring spacings are dependent on the sizes of the atoms in their backbones (8,10). Other studies showed that the degree of polymerization of the silicon polymer can be appreciable (6).

The combinations of properties possessed by these polymers were found to be quite unusual. For example, it was found that the silicon (6), germanium (8), aluminum (10), and gallium (10) polymers are stable at high temperatures under vacuum and that the silicon polymer is inert to concentrated sulfuric acid and to hydrofluoric acid (8). The aluminum and gallium polymers (10), in contrast to the silicon (6), germanium (8), and tin

polymers (12), were found to be volatile at high temperatures, apparently because they are subject to reversible depolymerization.

The second line of investigation leading to the development of conducting cofacial polymers centered on the synthetic and physical chemistry of conducting organic species. This line of investigation revealed that NiPcI_x and some other similar phthalocyanines have good conductivity when pressed into disks (13). In addition it showed that the iodinated octamethyltetrabenzporphine, $\text{Ni(OMTBP)(I}_3)_0.36$, contains parallel rods made of cofacially arranged rings and that it is highly conductive in the direction of its rods (14,15). Further, this line showed that $\text{NiPc(I}_3)_0.33$ also contains parallel rods of cofacial rings, Fig. 4, and that it too is highly conductive in the direction of its rods (16,17).

From this work it became clear that a close structural relationship exists between $\text{NiPc(I}_3)_0.33$ and the cofacial phthalocyanine polymers. This led to the discovery that $(\text{SiPcO})_n$, $(\text{GePcO})_n$, and $(\text{SnPcO})_n$ can be oxidized with iodine and that the resulting polymers, $(\text{SiPcOI}_x)_n$, $(\text{GePcOI}_x)_n$, and $(\text{SnPcOI}_x)_n$ are good conductors (18). Soon it was reported that $(\text{AlPcF})_n$ and $(\text{GaPcF})_n$ can be similarly iodinated and that the polymers obtained are likewise good conductors (19).

Recently the structure of $(\text{GaPcF})_n$ has been determined crystallographically (20), Fig. 5. As a result, both the qualitative and quantitative structural relationships for the $\text{GaPcF} - \text{NiPc(I}_3)_0.33$ pair are now fully known.

Other work has shown that fluorochromium phthalocyanine is a cofacial polymer too, and that iodination of it yields, not surprisingly, a conducting polymer (21). It has also been found that other oxidants can be used in place of iodine to make conducting polymers of the general type described,

e.g., bromine (18), various quinones (22), and various nitrosyls (23).

In the present work studies directed towards the synthesis and characterization of the 2,3-naphthalocyanine analogs of $(AlPcF)_n$ and $(GaPcF)_n$, i.e., $(AlNcF)_n$ and $(GaNcF)_n$, Fig. 6, and the corresponding iodinated polymers were undertaken. It was anticipated that the two iodinated polymers, if they could be made, would prove to be good conductors. (This set of uniodinated and iodinated polymers was chosen as an objective rather than one of the sets of isomeric 1,2-naphthalocyanine polymers because it was felt that the greater symmetry which these polymers would have would be generally advantageous.)

Information important to the initiation of this work was provided by three previous studies of naphthalocyanines. The earliest of these indicated that metal 2,3-naphthalocyanines could be made and that the metal-free and metal 1,2-naphthalocyanines could be isolated (24). The two later studies showed that metal-free and metal 2,3-naphthalocyanines could be isolated and yielded useful information about various members of this series including information on several aluminum and gallium species (25, 26).

Synthesis of Fluoroaluminum and Fluorogallium 2,3-Naphthalocyanine

The routes used to make fluoroaluminum and fluorogallium 2,3-naphthalocyanine were based to an important extent on procedures developed in earlier work on aluminum and gallium 2,3-naphthalocyanines (25) and phthalocyanines (10). The aluminum fluoride was made by reacting $\alpha, \alpha, \alpha', \alpha'$ -tetrabromo-o-xylene with fumaronitrile and sodium iodide, reacting the resulting 2,3-dicyanonaphthalene with aluminum chloride, and treating the product with sulfuric acid, ammonium hydroxide, and water. Additional steps involved reacting the hydrolysis product with chlorotri-

n-hexylsilane, recrystallizing the resulting siloxide, treating the recrystallized siloxide with hydrofluoric acid, and, finally, heating the acid-treated product under vacuum. The recrystallized siloxide and the fluoride gave satisfactory elemental analyses.

The gallium fluoride was made in a generally similar way. However, tri-n-hexylsilanol was used for the preparation of the siloxide instead of the corresponding chlorosilane because use of the latter resulted in the formation of the chloride instead of the siloxide. Elemental analysis of the final product yielded satisfactory results. (The recrystallized siloxide intermediate contained some μ -oxo dimer but this did not interfere.)

Properties and Structures of Fluoroaluminum and Fluorogallium 2,3-Naphthalocyanine

The two fluorides are dark green when finely divided. They are, as expected, stable to handling and storage. They are also stable under vacuum at temperatures in excess of 500°C. However, unlike $(AlPcF)_n$ and $(GaPcF)_n$ (10), they do not sublime perceptibly at high temperatures under vacuum (this is not surprising because even iron 2,3-naphthalocyanine does not sublime readily under these conditions (27)). Both fluorides give infrared spectra of the expected kind, Fig. 7, and both give multiline X-ray powder patterns. The pattern of the aluminum fluoride has a significant line corresponding to an interplanar spacing of 3.54 Å while that of its gallium analog has a significant line corresponding to a spacing of 3.69 Å.

On the basis of the properties which these fluorides exhibit and various close relationships which they have with $(AlPcF)_n$ and $(GaPcF)_n$, it is clear that they are structural analogs of these polymers and thus are

the polymers sought as the initial objective of the work. It appears from the X-ray data that the ring-ring spacing is 3.54 \AA in the aluminum polymer, and 3.69 \AA in the gallium polymer. Presumably, as in the case of $(\text{GaPcF})_n$ (20), the backbones of both $(\text{AlNcF})_n$ and $(\text{GaNcF})_n$ are linear, and the fluorines are situated midway between the metal atoms.

Synthesis and Nature of Iodine-Doped Fluoroaluminum and Fluorogallium 2,3-Naphthalocyanine

Fluoroaluminum and fluorogallium 2,3-naphthalocyanine doped with small to significant amounts of iodine were prepared by treating $(\text{AlNcF})_n$ and $(\text{GaNcF})_n$ with iodine-pentane solutions having low to substantial iodine concentrations. When the iodine concentrations were low to moderate, the iodine was taken up rapidly and quantitatively.

The iodinated products are black when they contain moderate amounts of iodine and are finely divided. They are stable to handling under ordinary conditions. Both products yield infrared spectra that show strong electronic excitation absorptions, Fig. 7, and Raman spectra that show strong lines in regions in which resonance enhanced lines for triiodide and pentaiodide ions are found (15,17,28), Fig. 8. Neither give evidence of having low molecular weights.

The currently available conductivity data for the products show that when their iodine levels are appreciable they have significant room-temperature, pressed-disk conductivities, Fig. 9. When their iodine levels are low to moderate, they have pressed-disk conductivities that are higher than those reported for their phthalocyanine analogs (29). (The conductivity observed for $(\text{AlNcF})_n$ itself is believed to be higher than the true value. It is thought that this is due to the presence of small amounts of impurities in the $(\text{AlNcF})_n$ used.)

On the basis of the data gathered and data available on related iodinated species (30), it is concluded that these iodinated products contain cationic chains having metal-fluorine backbones and cofacial rings, and very possibly also neutral, parent-polymer chains. The Raman data show that they contain both triiodide and pentaiodide ions. Accordingly it is apparent that these iodinated products are analogs of $(AlPcFI_x)_n$ and $(GaPcFI_x)_n$ and are the doped polymers sought.

Since the related neutral chains in $(GaPcF)_n$ are linear, the charged chains in these polymers are assumed to be linear. The charge distribution along some of them could well be nonuniform, although this is clearly open to question.

Despite the uncertainties involved, it is concluded that the charges of the chain repeat units that are charged are generally fractional. In addition it is inferred that the charges in the charged chains are associated with ligand-based orbitals and that the conductive pathways are of the ring-to-ring type.

Fluoroaluminum tetraphenylporphine and Fluoroaluminum Octaethylporphine

As a supplement to these efforts, studies of fluoroaluminum tetraphenylporphine and fluoroaluminum octaethylporphine, a previously reported compound (31), were carried out. The tetraphenylporphine was prepared by reacting metal-free tetraphenylporphine with lithium aluminum hydride, treating the product with water, and reacting the resultant with hydrofluoric acid. Further steps involved heating the material thus obtained in a vacuum sublimator and subliming the heated product. Elemental analysis of the resulting fluoride gave values in satisfactory agreement with the theoretical values. The octaethylporphine was prepared in a similar way.

When finely divided, the tetraphenylporphine is purple while the octaethylporphine is dark red. Both fluorides are stable to handling and storage and both are relatively volatile: the tetraphenylporphine subliming at about 300°C under vacuum and the octaethylporphine at about 270°C under vacuum. Neither, in contrast to their phthalocyanine and naphthalocyanine analogs, give powder patterns with lines that can be confidently attributed to ring-ring interplanar separations. Further, neither of them take up iodine from iodine-pentane solutions.

It thus appears that both fluorides are monomeric. This leads to the conclusion that Al(TPP)F contains square-pyramidal aluminum and, as suggested before (32), that Al(OEP)F also does, Fig. 10. Very likely the nonpolymeric nature of these fluorides is attributable to the sterically hindered nature of the ligands involved. Since these fluorides are apparently nonpolymeric and are not easily iodinated, it is concluded that it may not be easy or even possible to transform them into fluorine-bridged, cofacial conducting polymers.

Related Iodinated Cofacial Polymers

Some time ago the polymer oxogermanium hemiporphyrine, $(\text{GehpO})_n$, Fig. 11, was made (33). Recently the corresponding silicon polymer has been made (22). As is apparent these polymers are structural analogs of $(\text{SiPcO})_n$ and $(\text{GePcO})_n$. However, they differ from these polymers in that NMR data (33), X-ray data (34,35), simple Hückel considerations (36), and molecular orbital calculations (22), all suggest that the π -electrons of the ring system from which the nonbackbone portions of the polymers can formally be constructed and from which they are actually synthesized are not extensively delocalized.

Iodinated analogs of these hemiporphyrazine polymers have also been made. These analogs, in contrast to the corresponding iodinated phthalocyanine polymers, are poor conductors (22). This result is consistent with the idea that the conductivity of ring-ring conducting polymers is correlated with the amount of π -electron delocalization in the ring system from which the peripheral part of the polymers can formally be constructed (37).

Discussion

As already indicated a considerable amount of work has been done on cofacial conducting polymers apparently having fractionally oxidized repeat units and ring-ring conducting pathways. In summary, the data gathered show that in a polymer of this type a correlation exists between conductivity and level of oxidation (18,29), and suggest that in a set of such polymers correlations exist between conductivity and closeness of ring approach (18,29) and between conductivity and amount of precursor-ring π -electron delocalization (37).

As is evident, the data presented here illustrate further the correlation which exists in this type of cofacial conducting polymer between conductivity and oxidation level. They also provide additional data pointing to the existence of correlations between conductivity and ring approach and between conductivity and precursor-ring π -electron delocalization.

Whether a relationship exists between conductivity and ring size in a polymer of this type cannot be determined on the basis of the data at hand. However, it seems probable that this is the case. Similarly, whether a relationship exists between conductivity and the amount of overlap of the outer reaches of the rings also is not clear. Nevertheless, as already suggested (38), this too is likely.

On the basis of the data currently available, it seems likely that substantial electron delocalization, both along and across the chain, is necessary for high conductivity in polymers of the type under discussion. Whether the charge on the chains is associated with relatively localized or relatively delocalized orbitals is not clear.

In closing it is worth noting that these cofacial conducting polymers belong to a different class than such well-known conducting polymers as polythiazyl and doped polyacetylene (1) because the conducting pathway in the latter is along the backbone. These two classes can be distinguished by identifying the class to which the cofacial polymers belong as the conducting-ligand or conducting pendant group class, and that to which polythiazyl belongs as the conducting-backbone class.

Acknowledgment

We wish to thank Dr. Kenneth Wynne for helpful discussions and Dr. John Linsky for the micrograph of $(\text{SiPcO})_n$ shown. We also gratefully acknowledge support of this work by the Office of Naval Research and by the Graduate School Annual Alumni Fund of the University. The final versions of the ORTEP drawings were done by the Crystalytics Company.

References

1. K. J. Wynne and G. B. Street, Ind. Eng. Chem. Prod. Res. Dev., 27, 23 (1982).
2. P. A. Barrett, C. E. Dent, and R. P. Linstead, J. Chem. Soc., 1936, 1719.
3. J. E. Owen and M. E. Kenney, Inorg. Chem., 1, 334 (1962).
4. T. R. Janson, A. R. Kane, J. F. Sullivan, K. Knox, and M. E. Kenney, J. Am. Chem. Soc., 91, 5210 (1969).
5. D. R. Swift, Ph.D. Dissertation, Case Western Reserve University, Cleveland, OH, 1970.
6. R. D. Joyner and M. E. Kenney, Inorg. Chem., 1, 717 (1962).
7. R. D. Joyner and M. E. Kenney, J. Am. Chem. Soc., 82, 5790 (1960).
8. W. J. Kroenke, L. E. Sutton, R. D. Joyner, and M. E. Kenney, Inorg. Chem., 2, 1064 (1963).
9. T. R. Paul, J. P. Linsky, and M. E. Kenney, "Abstracts of Papers", 162nd National Meeting of the American Chemical Society, Washington, D.C., 1971, INORG 22.
10. J. P. Linsky, T. R. Paul, R. S. Nohr, and M. E. Kenney, Inorg. Chem., 19, 3131 (1980).
11. J. P. Linsky, Ph.D. Dissertation, Case Western Reserve University, Cleveland, OH, 1970.
12. W. J. Kroenke, Ph.D. Dissertation, Case Institute of Technology, Cleveland, OH, 1963.
13. J. L. Peterson, C. S. Schramm, D. R. Stojakovic, B. M. Hoffman, and T. J. Marks, J. Am. Chem. Soc., 99, 286 (1977).
14. T. E. Phillips and B. M. Hoffman, *ibid.*, 99, 7734 (1977).

15. T. E. Phillips, R. P. Scaringe, B. M. Hoffman, and J. A. Ibers, *ibid.*, 102, 3435 (1980).
16. C. J. Schramm, D. R. Stojakovic, B. M. Hoffman, and T. J. Marks, *Science* (Washington, D.C.), 200, 47 (1978).
17. C. J. Schramm, R. P. Scaringe, D. R. Stojakovic, B. M. Hoffman, J. A. Ibers, and T. J. Marks, *J. Am. Chem. Soc.*, 102, 6702 (1980).
18. K. F. Schoch, Jr., B. R. Kundalkar, and T. J. Marks, *ibid.*, 101, 7071 (1979).
19. P. M. Kusnesof, K. J. Wynne, R. S. Nohr, and M. E. Kenney, *J. Chem. Soc., Chem. Commun.*, 1980, 121.
20. R. S. Nohr and K. J. Wynne, *ibid.*, 1981, 1210.
21. P. M. Kusenesof, R. S. Nohr, K. J. Wynne, and M. E. Kenney, *J. Macromol. Sci. Chem.*, A16, 299 (1981).
22. C. W. Dirk, E. A. Mintz, K. F. Schoch, Jr., and T. J. Marks, *ibid.*, A16, 275 (1981).
23. P. Brant, R. S. Nohr, K. J. Wynne, and D. C. Weber, *Mol. Cryst. Liq. Cryst.*, 81, 255 (1982).
24. E. F. Bradbrook and R. P. Linstead, *J. Chem. Soc.*, 1936, 1744.
25. S. A. Mikhaleenko and E. A. Luk'yanets, *J. Gen. Chem. USSR (Engl. Transl.)*, 39, 2495 (1969).
26. A. Vogler and H. Kunkely, *Inorg. Chim. Acta*, 44, L209 (1980).
27. G. Magner, M. Savy, and G. Scarbeck, *This Journal*, 127, 1076 (1980).
28. R. C. Teitelbaum, S. L. Ruby, and T. J. Marks, *J. Am. Chem. Soc.*, 102, 3322 (1980).
29. R. S. Nohr, P. M. Kusenesof, K. J. Wynne, M. E. Kenney, and P. G. Siebenman, *ibid.*, 103, 4371 (1981).

30. B. N. Diel, T. Inabe, J. W. Lyding, K. F. Schoch, Jr., C. R. Kannewurf, and T. J. Marks, Polym. Prepr., Am. Chem. Soc., Div. Polym. Chem., 23, 124 (1982).
31. J. W. Buchler, L. Puppe, K. Rohbock, and H. H. Schneehage, Ann. N. Y. Acad. Sci., 206, 116 (1973).
32. J. W. Buchler, in "The Porphyrins", D. Dolphin, Ed., Vol. I, Chapter 10, Academic Press, New York (1978).
33. J. N. Esposito, L. E. Sutton, and M. E. Kenney, Inorg. Chem., 6, 1116 (1967).
34. H.-J. Hecht and P. Luger, Acta Crystallogr., Sect. B, B30, 2843 (1974).
35. W. Hiller, J. Strahle, K. Mitulla, and M. Hanack, Liebigs Ann. Chem., 1980, 1946.
36. L. E. Sutton and M. E. Kenney, Inorg. Chem., 6, 1169 (1967).
37. T. J. Marks, Ann. N.Y. Acad. Sci., 313, 594 (1978).
38. K. J. Wynne and R. S. Nohr, Mol. Cryst. Liq. Cryst., 81, 243 (1982).

Figure Captions

- Fig. 1. ORTEP drawing of $(\text{Me}_3\text{SiO})_2\text{MeSiO}(\text{SiPcO})_3\text{SiMe}(\text{OSiMe}_3)_2$ made with data gathered by Swift (5).
- Fig. 2. Structure of $(\text{SiPcO})_n$ (end groups probably OH in general).
- Fig. 3. Lattice image of a $(\text{SiPcO})_n$ crystal obtained by Linsky (11) giving evidence of the rigid-rod structure of $(\text{SiPcO})_n$.
- Fig. 4. ORTEP drawing of rod of cofacial rings in $\text{NiPc}(\text{I}_3)_{0.33}$ made with data gathered by Ibers and coworkers (17).
- Fig. 5. ORTEP drawing of $(\text{GaPcF})_n$ made with data obtained by Nohr and Wynne (20).
- Fig. 6. Structure of $(\text{AlNcF})_n$ (end group probably F in general).
- Fig. 7. Infrared spectra of Nujol mulls of $(\text{AlNcF})_n$ (top) and $(\text{AlNcFI}_{3.6})_n$ (bottom).
- Fig. 8. Raman spectrum ($\nu_0 = 5145 \text{ \AA}$) of $(\text{GaNcFI}_{1.2})_n$.
- Fig. 9. Ambient-temperature, pressed-disk electrical conductivity of $(\text{AlNcFI}_x)_n$ and $(\text{GaNcFI}_x)_n$ as a function of x.
- Fig. 10. Structures of $\text{Al}(\text{TPPF})$ and $\text{Al}(\text{OEP})\text{F}$.
- Fig. 11. Structure of $(\text{GehpO})_n$ (end groups probably OH in general).




Figure 1




Figure 2



Figure 3




Figure 4




Figure 5




Figure 6




Figure 7





Figure 8






Figure 10




Figure 11

Question #1. Dr. Frank Ludwig, Hughes Aircraft Co.

Would you expect to get n-doping also?

Answer: Clearly this is possible and some work has been done with potassium by others. However, the resulting materials are not very stable.

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 356B

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. C. L. Shilling Union Carbide Corporation Chemical and Plastics Tarrytown Technical Center Tarrytown, New York	1	Dr. G. Goodman Globe-Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. R. Soulen Contract Research Department Pennwalt Corporation 900 First Avenue King of Prussia, Pennsylvania 19406	1	Dr. E. Fischer, Code 2853 Naval Ship Research and Development Center Annapolis Division Annapolis, Maryland 21402	
Dr. A. G. MacDiarmid University of Pennsylvania Department of Chemistry Philadelphia, Pennsylvania 19174	1	Dr. Martin H. Kaufman Code 38506 Naval Weapons Center China Lake, California 93555	1
Dr. H. Allcock Pennsylvania State University Department of Chemistry University Park, Pennsylvania 16802	1	Dr. C. Allen University of Vermont Department of Chemistry Burlington, Vermont 05401	1
Dr. M. Kenney Case-Western University Department of Chemistry Cleveland, Ohio 44106	1	Professor R. Drago Department of Chemistry University of Florida Gainesville, FL 32611	1
Dr. R. Lenz University of Massachusetts Department of Chemistry Amherst, Massachusetts 01002	1	Dr. D. L. Venezky Code 6130 Naval Research Laboratory Washington, D.C. 20375	1
Dr. M. David Curtis University of Michigan Department of Chemistry Ann Arbor, Michigan 48105	1	COL R. W. Bowles, Code 100M Office of Naval Research 800 N. Quincy Street Arlington, Virginia 22217	1
NASA-Lewis Research Center Attn: Dr. T. T. Serafini, MS 49-1 21000 Brookpark Road Cleveland, Ohio 44135	1	Professor T. Katz Department of Chemistry Columbia University New York, New York 10027	1
Dr. J. Griffith Naval Research Laboratory Chemistry Section, Code 6120 Washington, D.C. 20375	1	Professor James Chien Department of Chemistry University of Massachusetts Amherst, Massachusetts 01002	1

TECHNICAL REPORT DISTRIBUTION LIST, 356B

	<u>No. Copies</u>	<u>No. Copies</u>
Professor Malcolm B. Polk Department of Chemistry Atlanta University Atlanta, Georgia 30314	1	
Dr. G. Bryan Street IBM Research Laboratory, K32/281 San Jose, California 95193	1	
Professor Michael Moran Department of Chemistry West Chester State College West Chester, Pennsylvania 19401	1	
Dr. K. Paciorek Ultrasystems, Inc. P. O. Box 19605 Irvine, California 92715	1	
Dr. D. B. Cotts SRI International 333 Ravenswood Avenue Menlo Park, California 94025	1	
Professor D. Seyferth Department of Chemistry Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	
Dr. Kurt Baum Fluorochem, Inc. 680 S. Ayon Avenue Azusa, California 91702	1	